

TC No.: MA2/A50/RQ025/25	Model No.: MARQ-2-50%	Date: 20-08-2025
Type and Capacity of Extinguisher	: MARQ-2-50%-Kanex ABC Dry Powder Fire Extinguisher Cap. 2 Kg.	
Batch Number	: MARQ50%2 025/25	
Batch Quantity	: 101.00 Nos.	
Serial Numbers	: 02401 To 2500 And 2405A	
Month of Manufacturing	: Aug/25	
Date of Inspection	: 20-08-2025	

Sr. Nos.	Cl. No.	Tests and Inspection	Requirements	Sampling	Observation
1	5.1.4	Extinguishing Agent	MAP 50% Dry Powder Conforms to IS 4308	One	Pass
2	5.3.2	Filling tolerance	±2% by Mass	One	Pass
3	6.1	Hydro test of the body	Test pressure 35 bar, Hold for 2.5 Min.	All	Pass
4	7.2	Effective discharge time	Approved fire rating is 1A:21B, hence Min. duration is 8sec. Sr. No. :02401	One	12 SEC.
5	7.2	Bulk range of Discharge	Approved fire rating is 1A:21B, hence Min. bulk range is 2m. Sr. No. :02401	One	2 Mtr.
6	3.8	Percentage of Discharge	Min. 85%, Sr. No. :02401	One	94%
7	7.4.1	Retention of Charge following partial discharge	The second pressure or weight shall not be less than 75% of the first after interruption of the discharge. Sr. No. :02402	One	95%
8	7.4.2	Leakage Test	Inverted Glass Jar/ Applying Soap Solution	All	Pass
9	9.2	Construction Requirements	As per IS 15683:2018	All	Pass
10	9.2.2	Burst test of body	Min. Burst pressure shall be 55 bar if break from body and shall be 80 bar if break from welding . Sr. No. :02405A	One	155 Bar
11	9.3	Carrying Handle	Requirements as per IS 15683:2018	All	Pass
12	9.4	Mounting Test	As per IS 15683:2018	All	Pass
13	9.5	Valves and Closures	As per IS 15683:2018	All	Pass
14	9.9	Method of Operation	Max. force require to operate the valve with full hand is 200N	One	161N
15	9.10.1	Safety Locking Devices	Force require to remove safety locking device is 20N-100N	Two	56N & 61N
16	9.10.6	Safety Locking Devices	Tamper indicator shall break with force not more than 70N & other requiremet as per IS 15683:2018	Two	53N & 58N
17	10.1	Color for body	As per Shade no. 538(P.O. Red) of IS 5 and blue band to be provide	All	Pass
18	--	Anticorrosive treatment & Painting	Phosphate treatment followed by Pure polyester Powder coating with DFT not less than 50μ.	All	(65-90)μ
19	10.2.1	Marking	As per IS 15683:2018	All	Pass
20	10.2.2	Operating Instructions	As per IS 15683:2018	All	Pass
21	10.2.3	Code symbols	As per IS 15683:2018	All	Pass
22	10.3	Inspection instruction	As per IS 15683:2018	All	Pass
23	Type tests	1)Resistance to Temp. changes 2)Impact test 3)Vibrations test 4)External Corrosion test 5)Tapping test 6)Intermittent discharge 7)Maximum Service Pressure 8)Crushing test 9)Pressure cycling 10) Fire performance test	As per IS 15683:2018	As per Scheme of testing	Pass
24	--	Dimensions and Completeness	Diameter: 106±5mm, Height: 380mm Approx, Thickness: 1.3mm Approx	All	Pass

Remarks: This is to certify that the ABC Dry Powder (Stored Pressure) type Fire Extinguisher of Capacity 2 kg. meets and conforms to the requirements of IS 15683:2018



Authorized Signatory