

|                                   |                                                                 |                  |
|-----------------------------------|-----------------------------------------------------------------|------------------|
| TC No.: A6/A50/RQ/025/26          | Model No.: KFARQ-6-50%                                          | Date: 20-01-2026 |
| Type and Capacity of Extinguisher | : KFARQ-6-50%-Kanex ABC Dry Powder Fire Extinguisher Cap. 6 Kg. |                  |
| Batch Number                      | : KFARQ50%6 025/26                                              |                  |
| Batch Quantity                    | : 101.00 Nos.                                                   |                  |
| Serial Numbers                    | : 02401 To 2500 And 2405A                                       |                  |
| Month of Manufacturing            | : Jan/26                                                        |                  |
| Date of Inspection                | : 20-01-2026                                                    |                  |

| Sr. Nos. | Cl. No.    | Tests and Inspection                                                                                                                                                                                                                     | Requirements                                                                                                                 | Sampling                 | Observation |
|----------|------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|------------------------------------------------------------------------------------------------------------------------------|--------------------------|-------------|
| 1        | 5.1.4      | Extinguishing Agent                                                                                                                                                                                                                      | MAP 50% Dry Powder Confirms to IS 4308                                                                                       | One                      | Pass        |
| 2        | 5.2        | Propellants                                                                                                                                                                                                                              | The propellants for stored pressure and cartridge operated extinguishers shall be air, carbon dioxide and nitrogen.          | All                      | Nitrogen    |
| 3        | 5.3.2      | Filling tolerance                                                                                                                                                                                                                        | ±2% by Mass                                                                                                                  | One                      | Pass        |
| 4        | 6.1        | Hydro test of the body                                                                                                                                                                                                                   | Test pressure 35 bar, Hold for 2.5 Min.                                                                                      | All                      | Pass        |
| 5        | 7.2        | Effective discharge time                                                                                                                                                                                                                 | Approved fire rating is 4A:144B, hence Min. duration is 15sec.<br>Sr. No. :02401                                             | One                      | 22 SEC.     |
| 6        | 7.2        | Bulk range of Discharge                                                                                                                                                                                                                  | Approved fire rating is 4A:144B, hence Min. bulk range is 2m.<br>Sr. No. :02401                                              | One                      | 5 Mtr.      |
| 7        | 3.8        | Percentage of Discharge                                                                                                                                                                                                                  | Min. 85%, Sr. No. :02401                                                                                                     | One                      | 95%         |
| 8        | 7.4.1      | Retention of Charge following partial discharge                                                                                                                                                                                          | The second pressure or weight shall not be less than 75% of the first after interruption of the discharge.<br>Sr. No. :02402 | One                      | 95%         |
| 9        | 7.4.2      | Leakage Test                                                                                                                                                                                                                             | Inverted Glass Jar/ Applying Soap Solution                                                                                   | All                      | Pass        |
| 10       | 9.2        | Construction Requirements                                                                                                                                                                                                                | As per IS 15683:2018                                                                                                         | All                      | Pass        |
| 11       | 9.2.2      | Burst test of body                                                                                                                                                                                                                       | Burst pressure shall be 55 bar if break from body and shall be 80 bar if break from welding .<br>Sr. No. :02405A             | One                      | 141 Bar     |
| 12       | 9.3        | Carrying Handle                                                                                                                                                                                                                          | Requirements as per IS 15683:2018                                                                                            | All                      | Pass        |
| 13       | 9.4        | Mounting Test                                                                                                                                                                                                                            | As per IS 15683:2018                                                                                                         | All                      | Pass        |
| 14       | 9.5        | Valves and Closures                                                                                                                                                                                                                      | As per IS 15683:2018                                                                                                         | All                      | Pass        |
| 15       | 9.8        | Hose Assemblies                                                                                                                                                                                                                          | Length of hose is 465mm and shall withstands a hydro pressure of 55 bar for at least 30 seconds.                             | One                      | 61 Bar      |
| 16       | 9.9        | Method of Operation                                                                                                                                                                                                                      | Max. force required to operate the valve with full hand is 200N                                                              | One                      | 161N        |
| 17       | 9.10.1     | Safety Locking Devices                                                                                                                                                                                                                   | Force required to remove safety locking device is 20N-100N                                                                   | Two                      | 57N & 62N   |
| 18       | 9.10.6     | Safety Locking Devices                                                                                                                                                                                                                   | Tamper indicator shall break with force not more than 70N & other requiremet as per IS 15683:2018                            | Two                      | 54N & 59N   |
| 19       | 10.1       | Color for body                                                                                                                                                                                                                           | Shade No. 538(P.O. Red) of IS 5 and blue band to be provided                                                                 | All                      | Pass        |
| 20       | --         | Anticorrosive treatment & Painting                                                                                                                                                                                                       | Phosphate treatment followed by Pure polyester Powder coating with DFT not less than 50μ.                                    | All                      | (65-90)μ    |
| 21       | 10.2.1     | Marking                                                                                                                                                                                                                                  | As per IS 15683:2018                                                                                                         | All                      | Pass        |
| 22       | 10.2.2     | Operating Instructions                                                                                                                                                                                                                   | As per IS 15683:2018                                                                                                         | All                      | Pass        |
| 23       | 10.2.3     | Code symbols                                                                                                                                                                                                                             | As per IS 15683:2018                                                                                                         | All                      | Pass        |
| 24       | 10.3       | Inspection instruction                                                                                                                                                                                                                   | As per IS 15683:2018                                                                                                         | All                      | Pass        |
| 25       | Type tests | 1)Resistance to Temp. changes<br>2)Impact test<br>3)Vibrations test<br>4)External Corrosion test 5)Tapping test<br>6)Intermittent discharge 7)Maximum Service Pressure 8)Crushing test<br>9)Pressure cycling<br>10)Fire performance test | As per IS 15683:2018                                                                                                         | As per Scheme of testing | Pass        |
| 26       | --         | Dimensions and Completeness                                                                                                                                                                                                              | Diameter: 150±5mm, Height: 530mm Approx, Thickness: 1.6mm Approx                                                             | All                      | Pass        |

**Remarks: This is to certify that the ABC Dry Powder (Stored Pressure) type Fire Extinguisher of Capacity 6 kg. meets and confirms to the requirements of IS 15683:2018**



**Authorized Signatory**